

BONDERITE C-NE 5088Known as P3 Neutrapon 5088
February 2021**PRODUCT DESCRIPTION**

BONDERITE C-NE 5088 provides the following product characteristics:

Technology	Industrial Cleaner
Product Type	Neutral Cleaner
Application	Parts Cleaning
Concentration on steel and nonferrous metals	5 to 20 g/L
Concentration on cast iron	15 to 30 g/L
Operating Temperature	50 to 80 °C spray process

BONDERITE C-NE 5088 is an aqueous neutral cleaner. It is composed of surfactants, salts of organic acids and hydrotropes. BONDERITE C-NE 5088 is free of solvents. Even despite high infiltration of coolants, the foaming behaviour of the product is unlikely to change. Change of colour is caused by raw material and has no impact on performance.

Application Areas:

Cleaning after cutting, stamping or pressing, simultaneously passivating steel, cast iron and nonferrous metals. BONDERITE C-NE 5088 is used in spray- or immersion processes.

TECHNICAL DATA

Appearance	clear, colourless liquid
Density at 20°C, DIN 51757	~1.05 g/cm ³
pH-value, 10 g/L in DI water, 20 °C DIN 51369	~8.6

DIRECTIONS FOR USE**Preliminary Statement:**

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Bath Make-up:

Before turning on the spray system preheating of the solution to application temperature is recommended to avoid interfering foam build-up.

Add the required amount carefully to the circulation system.

Corrosion protection is increased, if deionized water instead of tap water is applied and the work pieces are stored at low relative air humidity and shielded against weather exposure.

Operating Data:

Temperature	50 to 80°C
Duration of treatment	0.5 to 3 min

Bath Control:

BONDERITE C-NE 5088 solution is controlled by titration of the total alkalinity.

Feed, mL	100 mL
Titrant:	0.5 N hydrochloric or 0.5 N sulphuric acid
End point:	pH 3.6
Indicator:	Methyl orange
Titration factor (TF):	2.5

- Pipette 100 mL bath solution into a clean 300 mL Erlenmeyer-flask.
- Add 4 to 5 drops of indicator.
- Titrate the solution with 0.5 N hydrochloric or 0.5 N sulphuric acid.
- The endpoint will be shown by a colour change from orange to red (pH: 3.6).
- The mL of the spent titration are multiplied by the Titration factor to obtain the concentration in g/L.
- Divide this by 10 to get the value in %.

Classification:

Please refer to the corresponding **Material Safety Data Sheets** for details on:

Hazards identification
Transport information
Regulatory information

Storage:

Recommended Storage Temperature, °C	-4.9 to 40
Shelf-life, months	24



ADDITIONAL INFORMATION

Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products.** **Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.5