

**BONDERITE M-NT 400**Known as Alodine 400  
November 2022**PRODUCT DESCRIPTION**

BONDERITE M-NT 400 provides the following product characteristics:

<b>Technology</b>	Surface Treatment
<b>Product Type</b>	Conversion coating
<b>Application</b>	Steel, zinc and aluminium, Rinse & No-Rinse
Process components:	BONDERITE M-NT 400 BONDERITE M-NT 400 R-2 BONDERITE M-NT 400 R3 for spray BONDERITE M-NT 400 R IM for dip

BONDERITE M-NT 400 is a liquid product for a chrome-free conversion treatment of light metals as well as post passivation for phosphate layers. In aqueous solutions colourless conversion layers are produced on light metals in immersion and spray application. Both treatments provide an excellent corrosion resistance as well as very good adhesion properties for subsequent painting. BONDERITE M-NT 400 suitable to be used after preanodizing.

**DIRECTIONS FOR USE****Preliminary Statement:**

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

**Bath Make-up:**

For each 1,000 L of bath add to the DI-water whilst stirring:

BONDERITE M-NT 400 (immersion) 5 to 20 L  
BONDERITE M-NT 400 (spray) 5 to 20 L

For Aluminium conversion coating adjustment of pH at make up is not needed.

For other use the pH-value should be adjusted with 3% Ammonia solution.

Changes in the above mentioned process parameters may be necessary. They have to be evaluated individually and documented specifically for each line.

**Control Points:**

	<b>Conversion</b>	<b>Post-Passivation</b>
pH-value	2.4 to 4.0	4.0 to 4.5

Temperature, °C	20 to 40	20 to 40
Time, sec	30 to 90	30 to 90
Spray pressure, bar	0.5 to 1.5	0.5 to 1.5
Conductivity, $\mu$ S/cm	200 to 1,200	200 to 1,200

**Process Description:**

The typical operation method consists of the following steps:

1. Alkaline or acid etching
2. Rinsing
3. Acid Deoxidizing
4. Rinsing
5. Rinse with DI-Water
6. Conversion treatment with BONDERITE M-NT 400
7. Optional: Rinse, Humidifying nozzles (with DI water, < 30 microS/cm) or air blowing nozzles

**Bath Maintenance:**

The BONDERITE M-NT 400 bath is controlled by determination of the pH-value or the electrolytical conductivity.

The adjusted conductivity or pH-value of the passivation bath should be kept constant during the bath operation.

Iron and chromium ions in the passivation bath can impair the conversion layer quality.

The max. iron concentration should not increase 10 ppm and the max. chromium concentration should be less than 1 ppm. BONDERITE M-NT 400 bath can also be monitored by photometric determination of titanium concentration.

**Bath Replenishment:**For conversion:

The conductivity of the BONDERITE M-NT 400 bath decreases during the working process due to a product consumption.

An addition of the product adjusts the required conductivity.

If required, mainly in the spray lines, BONDERITE M-NT 400 R-2 can be used for a bath make up or replenishment in the conversion stage.

Our technical customer service will make for you a corresponding recommendation.

For post-passivation:

The pH-value of the BONDERITE M-NT 400 bath increases during the working process due to a product consumption. An addition of the product adjusts the required pH-value.



**General Recommendation:**

For the incoming BONDERITE M-NT 400 and BONDERITE M-NT 400 R-2 fluoride resistant plastic like hard PVC or PP should be chosen.

The bath containers for the BONDERITE M-NT 400 bath can be made of hard PVC (without softening agents) or stainless steel 1.4571 or 1.4301.

A different possibility would be the use of a steel container which has been lined with a fluoride resistant plastic.

Racks, fastening material and baskets should be made of aluminium, stainless steel (1.4571 or 1.4301) or plastic (hard PVC).

The spraying systems, pumps and heating facilities should be made of stainless steel (1.4571 or 1.4301).

BONDERITE M-NT 400 baths must be detoxified and neutralized before adding them to the normal waste water.

**Caution:**

BONDERITE M-NT 400 and BONDERITE M-NT 400 R-2 contain anionic copolymers!

BONDERITE M-NT 400 and BONDERITE M-NT 400 R-2 contain complex fluoro compounds!

Watch safety precautions! Shield eyes with tightly fitting safety glasses, wear rubber gloves and chemical resistant safety clothes.

Avoid contact with skin! Do not inhale vapours!

Read the safety information on the product label!

**Classification:**

Please refer to the corresponding **Material Safety Data Sheets** for details on:

**Hazards identification**

**Transport information**

**Regulatory information**

**Storage:**

Recommended Storage Temperature, °C 5 to 40

Shelf life, months 12

(in unopened original packaging)

**ADDITIONAL INFORMATION****Disclaimer**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products.** Henkel Corporation specifically disclaims any liability for **consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.3